

UPM BioMotion™	X10	X20	X30
STSA Surface Area [m²/g]	11	23	40
pH	6 - 10	6 - 10	6 - 10
Sulfur Content [%]	< 0.2	< 0.2	< 0.2
Benzo[a]pyrene [ppm]	< 0.1	< 0.1	< 0.1
Each of 22 FDA PAHs [ppm]	< 1	< 1	< 1
Loss on Drying [%]	< 3	< 3	< 3