

Grade	Softening Point [°C] (ASTM 28)	Color G# (ASTM D1544)	M.Viscosity 175°C MPas (ASTM D3236)	Application
C5 CL100	95-105	Max 4#	Max 750	Road Marking
C5 CL1102	95-105	Max 5#	Max 250	Road Marking
C5 CL1104	95-105	Max 3#	Max 650	HMA
CL6100	95-105	Max 4#	Max 650	HMA, PSA
C5 CL6200	92-98	Max 3#	Max 350	PSA tape
C5/C9 HB1300	90-96	Max 3#	Max 350	PSA tape
C5/C9 HA1090	95-105	3-5#	Max 90	HMA GLUE&PSA
C5/C9 HA1110	105-115	3-5#	Max 120	HMA GLUE&PSA
C5/C9 HA1115	110-120	3-5#	Max 130	HMA GLUE&PSA
C5/C9 HA1120	120-126	3-5#	Max 150	HMA GLUE&PSA