

LUBRIZOL PEARLSTICK™	Viscosity mPas(20°C (*)	Minimum Activation Temperature	Crystallization Rate (MQSA 12 B)	Thermoplasticity (MQSA 68 A)
45-40/08	650-950	Approx. 45°C	Very High	Medium
45-40/15	1300-1700	Approx. 45°C	Very High	Medium
45-40/19	1700-2100	Approx. 45°C	Very High	Medium
45-40/27	2500-2900	Approx. 45°C	Very High	Medium
45-50/18	1600-2000	Approx. 55°C	Extremely High	Medium-Low
45-50/22	2000-2400	Approx. 55°C	Extremely High	Medium-Low
45-50/29	2400-3200	Approx. 55°C	Extremely High	Medium-Low
45-60/03	200-400	Approx. 50°C	Extremely High	Low
45-60/08	650-950	Approx. 50°C	Extremely High	Low
45-60/14	1200-1600	Approx. 50°C	Extremely High	Low
45-60/18	1600-2000	Approx. 50°C	Extremely High	Low
45-60/25	2300-2700	Approx. 50°C	Extremely High	Low
45-80/16	1400-1800	N/A	Very Low	Low
45-90/03	150-450	Approx. 40°C	Low	Low
45-90/06	450-750	Approx. 40°C	Low	Low
45-90/12	1000-1400	Approx. 40°C	Low	Low