

Characteristic	ASTM Test method	N-539	N-550	N-650	N-660	N-772
<b>Oil adsorption</b> (ml/100g)	D 2414	111	121	122	90	65
<b>Iodine no.</b> (mg/g)	D 1510	43	43	36	36	30
<b>Ash</b> (% max.)	D 1506	0,5	0,5	0,5	0,5	0,5
<b>Sieve residue 325 mesh</b> (ppm max.)	D 1514	100	200	250	250	500
<b>Nitrogen surface area</b> (m <sup>2</sup> /g)	D 6556	38	40	36	35	32
<b>Appearance</b>	-	Black pellets	Black pellets	Black pellets	Black pellets	Black pellets