

Characteristic	ASTM Test method	N-550 LG	N-650 LG
Oil adsorption (ml/100g)	D 2414	121	122
Iodine no. (mg/g)	D 1510	43	36
Ash (% max.)	D 1506	0,5	0,5
Sieve residue 325 mesh (ppm max.)	D 1514	20	20
Nitrogen surface area (m ² /g)	D 6556	40	36
Appearance	-	Black pellets	Black pellets