

Grade	Rate of crystallization	Viscosity (ML 1+4 at 100°C)	Typical application/properties
DENKA A-30	Fast	20±3 (a)	Spray adhesives
DENKA A-70	Fast	40±3 (a)	General, low viscosity
DENKA A-90	Fast	48±4 (a)	General
DENKA A-100	Fast	57±4 (a)	General
DENKA A-120	Fast	67±5 (a)	High viscosity
DENKA A-400	Fast	500-1500 (b)	Extrem high viscosity
DENKA TA-85	Fast	44±5 (a)	Thiuram-stabilized
DENKA M-120	Medium	900 (c)	To be used with grades A and TA
DENKA M-130 L	Medium	1000-1500 (c)	To be used with grades A and TA
DENKA M 130 H	Medium	1510-2700 (c)	Like M130L, for high viscosity