

<b>LUBRIZOL PEARLBOND™</b>	<b>MFI (ISO 1133) (g/10min.)</b>	<b>Viscosity 160°C (ISO 1133) Pas</b>	<b>Shore Hardness (MQSA 70 A) °C</b>	<b>Thermoplasticity (MQSA 68 A)</b>	<b>Crystallization Rate (MQSA 12 B)</b>
ECO D590	30-60 (1)	930	80-85	Very High	Extremely High
100	15-30 (1)	700	64-68	Very High	Very High
101	30-60 (1)	380	63-67	Very High	Very High
103	60-100 (1)	190	60-64	Very High	Very High
104	4-10 (1)	2950	110-130	High	High
106	10-30 (1)	1150	85-110	Very High	High
120	15-30 (2)	550	62-66	Very High	
121	30-60 (1)	380	63-67	Very High	Extremely High
122	105-160 (2)	2200	65-69	Very High	Extremely High
123	60-100 (1)	180	60-64	Very High	Extremely High
180	10-30 (1)	620	65-71	Very High	Very High
125/H	35-55 (3)	890	130-140*	-	-
12 C 75	15-40 (4)	1050	125-135*	-	-